



Putting it to the test

NRCA conducts testing of moisture vapor reduction admixtures

by Mark S. Graham

NRCA has conducted limited testing of a moisture vapor reduction admixture intended to minimize a concrete roof deck's ability to pass and release moisture vapor. Some background and an overview of NRCA's testing and results follow.

What's an MVRA?

Concrete admixtures intended as MVRAs are specific chemicals added during concrete's batching and mixing to provide an additional chemical reaction during the concrete's hydration and curing process. MVRAs use the concrete mix's excess water and chlorides to create a calcium silicate hydrate gel within the concrete. The gel is said to fill the small pores and capillary openings in curing concrete, minimizing the concrete's ability to pass and release moisture vapor. The gel is intended to be permanent and integral throughout the concrete thickness.

MVRAs are available from numerous suppliers and typically added to a concrete mix at the concrete batch plant separately from any other admixtures. Some MVRA suppliers permit their MVRAs to be added to concrete mixers at job sites provided the concrete mixer's drum is rotated for a supplier's recommended minimum amount of time after dosage and before concrete discharge and placement.



Recommended MVRA dosages vary somewhat between suppliers but generally range from about 10 to 14 ounces per 100 pounds of cementitious material.

MVRAs reportedly have been used successfully to address moisture release affecting floor coverings over concrete slabs on grade and at intermediate floor levels.

Several suppliers also are promoting use of their MVRA products for concrete roof decks to address the roofing industry's concerns with moisture release. However, their product literature, including product testing and data, show little to no

applicability to roof decks.

For example, several manufacturers cite ASTM D5084, "Standard Test Methods for Measurement of Hydraulic Conductivity of Saturated Porous Materials Using a Flexible Wall Permeameter," as the basis for their water vapor transmission and permeability testing. This test applies to fully saturated (containing no air) soil and rock at a limited temperature range—conditions similar to below-grade applications—with little to no relevance to roof assembly components.

NRCA testing

NRCA obtained core specimens of newly poured, cast-in-place roof decks from a building project under construction. A unique aspect of this particular project is it had

multiple concrete roof decks areas—several with an MVRA and one without an MVRA. The concrete mix design was reported to be similar for all the concrete roof decks with the MVRA being the known variable.

NRCA submitted the concrete core specimens to RDH Building Science Laboratories in Waterloo, Ontario, for laboratory testing and analysis. RDH Building Science Laboratories is widely recognized for its building science and laboratory testing expertise.

The concrete core specimens were cut into approximately 1-inch-thick slices and conditioned (dried). Testing was conducted using ASTM E96, "Standard Test Methods for Water Vapor Transmission of Materials." ASTM E96 is the standard method for determining water vapor transmission of building materials. ASTM E96 also is referenced in the

For additional information about NRCA's previous permeability testing, see "The quest for dryness," June 2017 issue.

The data presented applies specifically to the specimens tested at their cured age and may not necessarily apply to all concrete mix designs and concrete roof decks.

NRCA's recommendations

Based on its testing, NRCA finds the use of an MVRA provides no measurable benefit in a concrete roof deck's ability to minimize the passage and release of moisture vapor.

NRCA maintains its previous recommendation: Designers should specify a high-bond strength vapor retarder be adhered directly to concrete roof decks in new construction situations. This recommendation also applies to concrete roof decks where an MVRA is used. For reroofing situations where an existing

	Deck 1 (no MVRA)		Deck 2 (with an MVRA)		Deck 3 (with an MVRA)	
Specimen No.	1-1	1-2	2-1	2-2	3-1	3-2
Permeability (U.S. perm)	1.9	1.8	3.7	3.4	3.7	3.8

Average tested permeability values

International Building Code® as the basis for determining whether a building material is vapor-permeable or serves as a vapor retarder.

The results of the ASTM E96 testing are shown in the figure.

Review of the test data shows average tested values for the non-MVRA specimens to be generally consistent with previous NRCA testing of concrete specimens of a similar cured age.

The test data for the MVRA specimens shows permeability values greater than those of the non-MVRA specimens; this indicates the MVRA specimens are more "vapor open" than the non-MVRA specimens. These test results contradict claims an MVRA minimizes concrete's ability to pass and release moisture vapor.

roof deck shows evidence of moisture-related problems, a high-bond strength vapor retarder also should be adhered directly to the deck. When a vapor retarder is used, roof system designs using mechanical fasteners penetrating the vapor retarder should be avoided.

Additional information about concrete roof decks is contained in Chapter 2-Roof Decks of *The NRCA Roofing Manual: Membrane Roof Systems—2019*. NRCA members can download the manual for free at shop.nrca.net. 📄🔍

MARK S. GRAHAM is NRCA's vice president of technical services.

[@MarkGrahamNRCA](https://twitter.com/MarkGrahamNRCA)

Businesses urged to enhance cybersecurity protections

The IRS, state tax agencies and the tax industry are urging business owners to boost cybersecurity protections against business identity theft, according to www.irs.gov.

Identity thieves are demonstrating sophisticated knowledge of the tax code and industry filing practices as they attempt to obtain data to file fraudulent returns. To protect taxpayers and their business returns, the IRS has taken steps to identify and prevent business identity theft.

As with fraudulent individual returns, certain signs may indicate a business has fallen victim to identity theft. Businesses, partnerships, and estate and trust filers should be alert to potential identity theft and contact the IRS if they experience any of the following issues:

- Extension-to-file requests are rejected because a tax return with the Employer Identification Number or Social Security Number already is on file.
- An e-filed return is rejected because a duplicate Employer Identification Number or Social Security Number already is on file.
- An unexpected receipt of a tax transcript or IRS notice is received by a filer that does not correspond to anything submitted by the filer.
- Expected and routine correspondence from the IRS does not arrive because a thief has changed the address.

Additional information regarding how to protect against identity theft is available at www.irs.gov/newsroom/security-summit.



Building safety programs to receive significant funding in 2020

Significant funding for building safety programs was included in federal spending legislation signed by President Trump Dec. 20, 2019. Before the appropriations agreement was approved, the International Code Council® supported its passage by engaging with lawmakers.

The building safety funding provisions include:

- A \$100 million increase to \$3.4 billion total for the Community Development Block Grant Program, which funds code adoption and enforcement activities at state and local levels
- A \$20 million increase to \$1.26 billion total for Perkins Act career and technical educational state grants
- An \$80 million increase in Federal Emergency Management Agency preparedness grants to \$2.9 billion total, including a \$35 million increase to \$560 million for the State Homeland Security Grant Program and a \$5 million increase to \$355 million for the Assistance to Firefighters Grant Program, Staffing for Adequate Fire & Emergency Response Grant Program, and Emergency Management Performance Grant Program, respectively
- A \$1.6 million increase to \$4.5 million total for WaterSense, which the International Green Construction Code® leverages and is supported by the International Accreditation Service and ICC Evaluation Service products
- A \$3 million increase to \$10 million total for the Department of Energy's Building Energy Codes Program, which supports the development and implementation of the International Energy Conservation Code®

In addition, the provisions included a \$167 million increase in funding for the National Institute of Standards and Technology. Notably, NIST's Science and Technical Research and Services received a \$29.5 million increase. The institute's disaster resilience grants also were preserved, and current funding levels will allow NIST's premise plumbing research to continue.

The legislation also extends the 45L tax credit for new homes that are 50% more efficient than the 2006 IECC from Dec. 31, 2017, to Dec. 31, 2020, and, during the same period, the 179D tax deduction for efficiency improvements to commercial buildings.

